

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

JA 0110758

AUG 1980



72286 C/41 M27

SUMITOMO METAL IND KK

SUMQ 20.02.79

*JS 5110-758

20.02.79-JA-019315 (26.08.80) C22c-38/24


High temp. creep resistant chromium steel - has controlled relationship between nitrogen and aluminium contents and includes Molybdenum, vanadium etc.

Steel which has a high creep strength for a long time at a high temp. partic. $>550^{\circ}\text{C}$, consists of C 0.02-0.22%, Si $<1.0\%$, Mn $<1.0\%$, Cr 5-13%, Mo 0.5-2.5%, V 0.01-0.5% and N 0.015-0.10%, additional Ni $<1.5\%$ and ≥ 1 of W $<1.5\%$, Ti, Zr, Nb and Ta $<0.5\%$ respectively and B $<0.05\%$, and the balance Fe with incidental impurities of Al $<0.02\%$ and satisfying the relation $\text{N}-0.5\text{Al} \geq 0.015\%$.

After normalising and tempering treatment, structure of the steel comprises fine chromium nitride, carbides of Mo and V and carbonitrides of W, Ti, Zr, Nb and Ta ptpd. and dispersed in a martensitic or ferrite-tempered martensitic matrix. (6pp53).

M(27-A4, 27-A4C, 27-A4M, 27-A4N, 27-A4V, 27-A4X).

106



J55110758

420

420/109
420/108
420/106